



CORTEC
CORPORATION

Environmentally Safe VpCI®/MCI® Technologies

VpCI®-330

DESCRIPTION(개요)

VpCI®-330은 사용이 간편한 투명한 저점도 방청제입니다. 실내 및 실외 지붕이 있는 장소의 금속에 대한 우수한 보호 기능을 제공합니다. 이 제품은 얇고 투명한 필름을 남깁니다.

금속 부품에는 추가적인 처리 또는 운송을 위해 거의 보이지 않는 오일 코팅이 필요합니다(예: 보호되어야 하지만 후속 오일 제거가 불가능하거나 바람직하지 않은 기타 금속 부품에 적용).


PACKAGING & STORAGE (포장 및 보관)

5gallon (19L) pails
55gallon(208L) drums
liquid totes, and bulk.

제품의 성능을 잘 유지하기 위해서는 원래의 포장으로 실내에 직사광선이 없는 곳에서 보관.
4-38 °C(0-100 °F)

보관기간: 2년

VpCI® METALWORKING PRODUCTS



FEATURES(특징)

- 불연성
- 투명하고 균질함(최소 4 ~ 60 °C (40 ~ 140 °F))
- 크롬산염, 아질산염, 인산염, 2차 아민 또는 OSHA 위험 성분을 포함하지 않음

BENEFITS(이점)

- 철 금속에 범용 부식 방지 기능을 제공하며 황금속과 호환
- 100% 상대습도 및 염화물과 같은 부식성 종류가 있는 경우에도 효과적으로 수행
- 휴대용 트리거 스프레이 병 또는 일반 스프레이 장비를 사용하여 쉽게 분사

APPLICATION(적용)

VpCI-330은 금속 표면에 분사, 담금, 압연 또는 브러싱할 수 있습니다. 휴대용 트리거 스프레이 병은 쉽게 사용할 수 있도록 잘 작동합니다.

TYPICAL PROPERTIES(표준 속성)

외관	특명 노랑 액체
필름 형태	투명한 오일 필름
비중	6.6-7.0 lb/gal (0.79-0.84 kg/L)
휘발점	82 °C(179 °F)
점도 40 °C(104 °F)	2.5 cPs

STANDARD TEST METHODS(표준 시험 결과)

Test Method	Description	Results
ASTM D1748	습윤상 시험	>800 hours
ASTM B117	염수분무테스트	24 hours
ASTM D130	Copper Strip Test	1a

4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC
info@cortecvci.com
https://www.cortecvci.com
https://www.cortecmetalworking.com



LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.